

IPC-4101 /98 /99 /101 /126 UL - File Number E41625

IS420 is a high performance 170°C glass transition temperature (Tg) FR-4 system for multilayer Printed Wiring Board (PWB) applications where maximum thermal performance and reliability are required.

PRODUCT FEATURES

Industry Recognition

- UL File Number: E41625
- Qualified to UL's MCIL Program
- RoHS Compliant

Performance Attributes

- Lead-free assembly compatible

Processing Advantages

- FR-4 process compatible
- UV blocking and AOI fluorescence

PRODUCT AVAILABILITY

Standard Material Offering: Laminate

- 2 to 93 mil (0.05 to 2.4 mm)
- Available in full size sheet or panel form

Copper Foil Type

- HTE Grade 3
- RTF (Reverse Treat Foil)

Copper Weight

- ½ to 2 oz (18 to 70 µm) available
- Heavier copper available
- Thinner copper foil available

Standard Material Offering: Prepreg

- Roll or panel form
- Tooling of prepreg panels

Glass Fabric Availability

- E-glass
- Square weave glass

IS420 laminate and prepreg products are manufactured with a unique high performance multifunctional epoxy resin, reinforced with electrical grade (E-glass) glass fabric. This system provides improved thermal performance and low expansion rates in comparison to traditional FR-4 while retaining FR-4 processability.

In addition to this superior thermal performance, the mechanical, chemical and moisture resistance properties all equal or exceed the performance of traditional FR-4 materials. The IS420 system is also laser fluorescing and UV blocking for maximum compatibility with Automated Optical Inspection (AOI) systems, optical positioning systems and photoimable solder mask imaging.

PRODUCT ATTRIBUTES



HIGH THERMAL
RELIABILITY



LEGACY

ORDERING INFORMATION:

Contact your local sales representative or contact info@isola-group.com for further information.

Isola Group

6565 West Frye Road Chandler,
AZ 85226 Phone: 480-893-6527
Fax: 480-893-1409

Isola Asia Pacific

(Hong Kong) Ltd. 12/F,
Kin Sang Commercial Centre,
49 King Yip Street, Kwun Tong,
Kowloon,
Hong Kong Phone: 852-2418-1318
Fax: 852-2418-1533

Isola GmbH

Isola Strasse 2 D-52348 Düren,
Germany Phone: 49-2421-8080
Fax: 49-2421-808164

Typical Values Table

Property	Typical Value	Units		Test Method
		Metric (English)		IPC-TM-650 (or as noted)
Glass Transition Temperature (Tg) by DSC	170		°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss	350		°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	60 >15	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	45 230 2.8	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	13/14	ppm/°C	2.4.24C
Thermal Conductivity		0.4	W/m-K	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	4.24 4.17 4.04 3.92 3.92	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Df, Loss Tangent	A. @ 100 MHz B. @ 1 GHz C. @ 2 GHz D. @ 5 GHz E. @ 10 GHz	0.0150 0.0161 0.0210 0.0250 0.0250	—	2.5.5.3 2.5.5.9 Bereskin Stripline Bereskin Stripline Bereskin Stripline
Volume Resistivity	A. After moisture resistance B. At elevated temperature	3.0×10^8 7.0×10^8	MΩ-cm	2.5.17.1
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 3.0×10^6 2.0×10^8	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		115	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		54 (1350)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.14 (6.5) 1.25 (7.0) 1.25 (7.0) 1.14 (6.5)	N/mm (lb/inch)	2.4.8C 2.4.8.2A 2.4.8.3 2.4.8.3
Flexural Strength	A. Length direction B. Cross direction	82.7 60.9	ksi	2.4.4B
Moisture Absorption		0.15	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Relative Thermal Index (RTI)		130	°C	UL 796

NOTES

Visit our site <http://www.isola-group.com> for more details.

Revisions:

A: Initial release - 4/17

B: Corrected units for Flexural and Tensile Strength - 8/18

C: Change MOT to RTI 5/19

D: Added /126 slash sheet 02/20

Isola, the Isola logo, Astra, Chronon, GETEK, I-Fill, IsoDesign, IsoStack, I-Speed, I-Tera, Polyclad, Stratus, TerraGreen, and The Base for Innovation are registered trademarks or trademarks of ISOLA USA Corp. in the United States and in other countries.

Copyright © 2021 Isola Group. All rights reserved.